



Better Quality Better Service

Technical Data Sheet

Ningbo Jinhai Chenguang Chemical Corporation

PC: 315207

No. 2666, Binhai Road, Ningbo Petrochemical
Economic and Technological Development Zone,
Zhejiang Province, China.

TEL: 0086-574-8765 3737

FAX: 0086-574-8765 7399

Jan., 2025

Thermoplastic Elastomer SIS HAISIS™ JH-9411

HAISIS™ **JH-9411** is a clear, linear triblock copolymer based on styrene and isoprene, with a polystyrene content of 44%. **JH-9411** is used as an ingredient in formulating adhesives, sealants and coatings. It also can be used as a modifier of thermoplastics and in compound formulations.

Product Specifications:

Test Items	Unit	Sales specification range
Polystyrene Content	Wt%	42 TO 46
Di-block Content	Wt%	<1
Melt Flow Rate	g/10min	35 TO 45
Color	YI	≤6
Tensile Strength	MPa	≥14
Elongation at Break	%	≥700
Volatile Matter	Wt%	≤0.70
Ash	Wt%	≤0.20

Typical Value:

Test Items	Unit	Value
Polystyrene Content	Wt%	43.9
Di-block Content	Wt%	<1
Melt Flow Rate, 200℃ 5kg	g/10min	40
Color	YI	4
Hardness	Shore A	90
Solution Viscosity	CPS	106
Tensile Strength	MPa	18.5
Elongation at Break	%	755
Volatile Matter	Wt%	0.54
Ash	Wt%	0.08
Mn (SIS)	g/mol	60000
D	/	1.01



Applications

- a) Pressure sensitive adhesives
- b) Sealants
- c) Coatings
- d) Modifiers.

Packaging and supply

Package:

Packing size: 20kg in paper-plastic composite bags or PE bags;

Super sack packaging: From 450kg to 1000kg in one sack upon the customers' requirements.

Supply:

Supplied on shrink-wrapped pallets of 40 bags or 50bags each, from Jinhai's facilities in China.

Regulatory/Classifications

CAS No. 25038-32-8

USA - Food and Drug Administration (FDA)

When used unmodified for food contact applications the styrene-isoprene block copolymer product(s) listed in the table above will comply with the U.S. Food, Drug, and Cosmetic Act as amended under Food Additive Regulation 21 CFR 177.1810 (b)(2) with the following limitations: In addition, the styrene-isoprene block copolymer product(s) listed in the table above will also comply with the following:

US FDA: 21 CFR 175.105	Adhesives
21 CFR 177.2600	Rubber articles intended for repeated use.
21 CFR 175.125	Pressure sensitive adhesives.
21 CFR 175.300	Resinous and polymeric coatings
21 CFR 176.170	Components of paper and paperboard in contact with aqueous and fatty foods
21 CFR 176.180	Components of paper and paperboard in contact with dry food
21 CFR 175.320:	Resinous and Polymeric Coating for Polyolefin Films
21 CFR 177.1210:	Closures with Sealing Gaskets for Food Containers.

Other regulatory information is available on request.

Storage

Pelletized forms of products may block or lump in hot weather climates or if stored near heat sources. Inside storage is recommended and keep at temperature not exceeding 30 °C. The useful life of this product can be affected by storage and handling conditions. When stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, the shelf life of this product is estimated to continue to meet applicable sales specifications for 24 months from the date of manufacture. Shelf Life is a guide not an absolute value. The product should be reanalyzed for critical properties at the end of its shelf life to see if it meets specification for use.

Product Safety

Read and understand the Material Safety Data Sheet before using HAISIS™ JH-9411.